


# PIETRO



## Product Information

Usage classification	EN ISO 10874 EN 685		23 - 31
Wear layer	EN ISO 24340 EN 429		0,25 mm
Total thickness	EN ISO 24346 EN 428		2,25 mm
Total weight	EN ISO 23997 EN 430		1700 g/m <sup>2</sup>
Standard widths	EN ISO 24341 EN 426		4 - 5 m
Standard length	EN ISO 24341 EN 426		25 m

## Technical Information

Light stability	EN ISO 105 B02		≥ 6
Dimensional stability	EN ISO 23999 EN 434		≤ 0,40 %
Underfloor heating	EN 12667		Suitable
Residual indentation	EN ISO 24343-2 EN 433		≤ 0,35 mm
Impact sound	EN ISO 717/2		Δ Lw 13 dB
Reaction to fire	EN 13501-1		Bfl/S1
Slip resistance	DIN 51130		R10
Dynamic coefficient of friction	EN 13893		> 0,6